

## AlphaGary Evoprene™ 3275 Standard SBS Thermoplastic Elastomer Compound

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_AlphaGary-Evoprene-3275-Standard-SBS-Thermoplastic-Elastomer-Compound.php](http://www.lookpolymers.com/polymer_AlphaGary-Evoprene-3275-Standard-SBS-Thermoplastic-Elastomer-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	ISO 2782
Viscosity Measurement	9.0 @Temperature 150 °C	9.0 @Temperature 302 °F	Kg/cm <sup>2</sup> ; Macklow-Smith extrusion rheometer

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	ISO 868
Tensile Strength	5.20 MPa	754 psi	ISO 37
Elongation at Break	830 %	830 %	ISO 37
100% Modulus	0.00140 GPa	0.203 ksi	ISO 37
Tear Strength	30.0 kN/m	171 pli	ISO 34-B
Compression Set	35 % @Temperature 22.0 °C, Time 259000 sec	35 % @Temperature 71.6 °F, Time 72.0 hour	ISO 815

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	55.0 - 60.0 °C	131 - 140 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not specified

Descriptive Properties	Value	Comments
Bonds with	Polystyrene	
Chemical Resistance	Acetone	Moderate
	Acids up to 80%	Moderate
	Alcohol	Good

Descriptive Properties	Value	Comments
	Brake fluid	Moderate
	Chlorinate solvents	Poor
	Diesel	Poor
	Ethylene glycol	Excellent
	Gasoline	Poor
	Salt solution	Good
	Soda lye	Moderate
	Water, 23°C	Good
	Water, 95°C	Poor
Ozone Resistance	Fail - Crack	100 pphm / 200 hrs / 20% strain
Transparency	Transparent	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China