

AlphaGary GW 2280 M VW1 LCF Flame Retardant Polyvinyl Chloride

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

75°C or 80°C low temperature rated flexible jacketing compound intended for UL 62 application

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-GW-2280-M-VW1-LCF-Flame-Retardant-Polyvinyl-Chloride.php

Mechanical Properties	Metric	English	Comments
Tensile Strength	15.2 MPa	2200 psi	
Elongation at Break	300 %	300 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-30.0 °C	-22.0 °F	
Oxygen Index	26 %	26 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China