

AlphaGary Garaflex™ O 9940 DWN-R Olefinic Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO)

Material Notes:

Garaflex™ O is a flame retarded, olefinic thermoplastic elastomer 125°C rated flame retardant olefinic TPE with excellent dry and wet electrical stability

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-Garaflex-O-9940-DWN-R-Olefinic-Thermoplastic-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	44 - 53	44 - 53	
Tensile Strength	15.2 MPa	2200 psi	
Elongation at Break	550 %	550 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	
Oxygen Index	35 %	35 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China