

AlphaGary Garaflex™ O 9940 SA Olefinic Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO) , Polyolefin , Polyolefin, Wire/Cable Grade

Material Notes:

Garaflex™ O is a flame retarded, olefinic thermoplastic elastomer 105°C rated flame retardant olefinic TPE for flat ribbon cable and heat tracing cable

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-Garaflex-O-9940-SA-Olefinic-Thermoplastic-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	43 - 51	43 - 51	
Tensile Strength	13.8 MPa	2000 psi	
Elongation at Break	500 %	500 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-53.0 °C	-63.4 °F	
Oxygen Index	30 %	30 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China