

AlphaGary Garathane™ X 94-350-B UV-DG2 Polyurethane based compound

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

90°C rated flame retardant, polyether based, polyurethane compound

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-Garathane-X-94-350-B-UV-DG2-Polyurethane-based-compound.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82 - 87	82 - 87	
Tensile Strength	11.0 MPa	1600 psi	
Elongation at Break	600 %	600 %	ASTM D412

Thermal Properties	Metric	English	Comments
Oxygen Index	30 %	30 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China