

AlphaGary PVC GM 5075 Polyvinyl Chloride Thermoplastic

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

A 105°C rated, lead & cadmium free, UL-94 V2 molding compound

Order this product through the following link:

http://www.lookpolymers.com/polymer_AlphaGary-PVC-GM-5075-Polyvinyl-Chloride-Thermoplastic.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75 - 86	75 - 86	
Tensile Strength	10.3 MPa	1500 psi	
Elongation at Break	280 %	280 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-25.0 °C	-13.0 °F	
Flammability, UL94	V-2	V-2	
Oxygen Index	26 %	26 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China