

## AlphaGary PVC GM 8015-O Natural LCF Polyvinyl Chloride Thermoplastic

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

**Material Notes:**

A lead / cadmium free, 105°C, UL-94 V-0 rated, electrical grade molding compound

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_AlphaGary-PVC-GM-8015-O-Natural-LCF-Polyvinyl-Chloride-Thermoplastic.php](http://www.lookpolymers.com/polymer_AlphaGary-PVC-GM-8015-O-Natural-LCF-Polyvinyl-Chloride-Thermoplastic.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	89 - 95	89 - 95	
Tensile Strength	13.8 MPa	2000 psi	
Elongation at Break	280 %	280 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-18.0 °C	-0.400 °F	
Flammability, UL94	V-0	V-0	
Oxygen Index	28 %	28 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China