

Amco PRIMATOP HDPE 002955 Phillips Process Hexene Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

PRIMATOP HDPE 002955 has a high melt strength, excellent stiffness, and excellent stress crack resistance. Applications include large part blow molding resin and sheet extrusion thermoforming. Former A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Amco-PRIMATOP-HDPE-002955-Phillips-Process-Hexene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in ³	ASTM D1505
ESCR 100% Igepal®	35 hour	35 hour	Condition B, F50; ASTM D1693
	45 hour	45 hour	Condition A, F50; ASTM D1693
Melt Index of Compound	0.25 g/10 min	0.25 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	2" per min, Type IV; ASTM D638
Elongation at Break	>= 600 %	>= 600 %	2" per min, Type IV; ASTM D638
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -84.4 °C	<= -120 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China