

## Amco PRIMATOP HDPE 003955BAS Hexene Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

### Material Notes:

HDPE 003955BAS features excellent stiffness, stress crack resistance properties, and antistat. Applications include blow molding and sheet extrusion thermoforming. Former A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Amco-PRIMATOP-HDPE-003955BAS-Hexene-Copolymer.php](http://www.lookpolymers.com/polymer_Amco-PRIMATOP-HDPE-003955BAS-Hexene-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in <sup>3</sup>	ASTM D1505
ESCR 100% Igepal®	35 hour	35 hour	Condition B, F50; ASTM D1693
	45 hour	45 hour	Condition A, F50; ASTM D1693
Melt Index of Compound	0.35 g/10 min	0.35 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	2" per min, Type IV; ASTM D638
Elongation at Break	>= 600 %	>= 600 %	2" per min, Type IV; ASTM D638
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -118 °C	<= -180 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China