

Amco PRIMATOP PP CO 350-10 RC Clarified Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Features:excellent processingimpactclarityanti-statApplications:rigid packaginghousewaresFormer A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Amco-PRIMATOP-PP-CO-350-10-RC-Clarified-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Index of Compound	35 g/10 min @Temperature 230 °C	35 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Yield	32.1 MPa	4650 psi	50 mm/min; ASTM D638
Elongation at Yield	12.5 %	12.5 %	50 mm/min; ASTM D638
Flexural Modulus	1.21 GPa	175 ksi	1.3 mm/min, 1% Secant; ASTM D790
Izod Impact, Notched	0.507 J/cm @Temperature 22.8 °C	0.950 ft-lb/in @Temperature 73.0 °F	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China