

Amco PRIMATOP PP CO 350-20 Impact Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

PP CO 350-20 has easy mold flow and excellent dimensional stability. It is used in thin walled injection molded applications. Former A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Amco-PRIMATOP-PP-CO-350-20-Impact-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D1505
Melt Index of Compound	36 g/10 min @Temperature 230 °C	36 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	104	104	ASTM D785
Tensile Strength, Yield	23.4 MPa	3400 psi	50 mm/min; ASTM D638
Flexural Modulus	1.02 GPa	148 ksi	1% Secant; ASTM D790
Izod Impact, Notched	1.01 J/cm @Temperature 22.8 °C	1.90 ft-lb/in @Temperature 73.0 °F	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China