

## Amco PRIMATOP PP CO 350-40 Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

PP CO 350-40 features impact resistance and low temperature stiffness. Applications include injection molding and containers. Former A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Amco-PRIMATOP-PP-CO-350-40-Polypropylene-Copolymer.php](http://www.lookpolymers.com/polymer_Amco-PRIMATOP-PP-CO-350-40-Polypropylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D792
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Melt Index of Compound	35 g/10 min	35 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.7 MPa	3000 psi	2 in/min; ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Modulus	0.931 GPa	135 ksi	0.05 in/min, 1% Secant; ASTM D790
Izod Impact, Notched	1.92 J/cm	3.60 ft-lb/in	Method A; ASTM D256
	@Temperature 22.8 °C	@Temperature 73.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China