

Amco PRIMATOP PP HOMO 201NA Injection Molding Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Features:nucleationanti-statlow viscosityexcellent processabilityexcellent stiffnessminimal odor or tasteApplications:thin wall partsclosuressmall appliancesFormer A-Top Polymers product; part of Amco product line since 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Amco-PRIMATOP-PP-HOMO-201NA-Injection-Molding-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ASTM D1505
Melt Index of Compound	20 g/10 min @Temperature 230 °C	20 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	50 mm/min; ASTM D638
Elongation at Yield	6.5 %	6.5 %	50 mm/min; ASTM D638
Flexural Modulus	1.86 GPa	270 ksi	1.3 mm/min, 1% Secant; ASTM D790
Izod Impact, Notched	0.320 J/cm @Temperature 22.8 °C	0.600 ft-lb/in @Temperature 73.0 °F	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China