

Americas Styrenics EA6740 High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Product Characteristics Very good printability Matte surface finish High heat distortion temperature Good low temperature toughness Food Contact Compliant Typical Applications Packaging and one-time use items Printed toys and games Point of purchase displays Silk screen printing Information provided by Americas Styrenics LLC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Americas-Styrenics-EA6740-High-Impact-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	3.2 g/10 min @Load 5.00 kg, Temperature 200 °C	3.2 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	99	99	ASTM D785
Tensile Strength at Break	19.3 MPa	2800 psi	ASTM D638
Tensile Strength	18.6 MPa	2700 psi	ASTM D638
Elongation at Break	75 %	75 %	ASTM D638
Tensile Modulus	1.59 GPa	230 ksi	ASTM D638
Flexural Strength	29.0 MPa	4200 psi	ASTM D790
Flexural Modulus	1.59 GPa	230 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	compression molded; ASTM D256
	1.44 J/cm	2.70 ft-lb/in	injection molded; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	88.9 °C	192 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	81.1 °C	178 °F	ASTM D648
Vicat Softening Point	100 °C	212 °F	ASTM D1525

Thermal Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China