

## Americas Styrenics STYRON® 487R High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

### Material Notes:

Product Characteristics Toughness Heat resistance Good stiffness Food Contact Compliant UL Classification 94HB Typical

Applications Lids Appliances Packaging/disposables Housewares Information provided by Americas Styrenics LLC.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Americas-Styrenics-STYRON-487R-High-Impact-Polystyrene.php](http://www.lookpolymers.com/polymer_Americas-Styrenics-STYRON-487R-High-Impact-Polystyrene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	2.8 g/10 min @Load 5.00 kg, Temperature 200 °C	2.8 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	ASTM D785
Tensile Strength at Break	24.1 MPa	3500 psi	ASTM D638
Tensile Strength	24.8 MPa	3600 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Tensile Modulus	2.00 GPa	290 ksi	ASTM D638
Flexural Strength	33.8 MPa	4900 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	compression molded; ASTM D256
	1.23 J/cm	2.30 ft-lb/in	injection molded; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	88.9 °C	192 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	79.4 °C	175 °F	ASTM D648
Vicat Softening Point	101 °C	214 °F	ASTM D1525

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**