

Americas Styrenics STYRON® 498 High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Product Characteristics High gloss High impact Food Contact Compliant UL Classification 94HB Typical

Applications Appliances Medical Housewares Consumer electronics Information provided by Americas Styrenics LLC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Americas-Styrenics-STYRON-498-High-Impact-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	3.5 g/10 min @Load 5.00 kg, Temperature 200 °C	3.5 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	114	114	ASTM D785
Tensile Strength at Break	29.6 MPa	4300 psi	ASTM D638
Tensile Strength	35.9 MPa	5200 psi	ASTM D638
Elongation at Break	45 %	45 %	ASTM D638
Tensile Modulus	2.24 GPa	325 ksi	ASTM D638
Flexural Strength	48.3 MPa	7000 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	0.854 J/cm	1.60 ft-lb/in	compression molded; ASTM D256
	1.07 J/cm	2.00 ft-lb/in	injection molded; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	93.3 °C	200 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.8 °C	181 °F	ASTM D648
Vicat Softening Point	105 °C	221 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China