

Ametek Molybdenum-Copper Composite AMC 8020

Category : Metal , Nonferrous Metal , Molybdenum Alloy , Refractory Metal

Material Notes:

Information supplied by Ametek Specialty Metal Products. The material is available as finished parts with the following maximum dimensions: Width: 6 inches (152 mm) Thickness: 0.150 inches (3.8 mm) Length: 8 inches (203 mm) These composites of molybdenum and copper have many applications in electronic devices. The excellent thermal conductivity and low thermal expansion make them ideal for: chip mounting, heat sinks, circuit board cores, lids or covers, or thermal spreaders. The material can be machined into shapes and readily plated if required. AMETEK's wrought powder metallurgy composites have superior through-thickness thermal conductivity versus other products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-Molybdenum-Copper-Composite-AMC-8020.php

Physical Properties	Metric	English	Comments
Density	9.94 g/cc	0.359 lb/in ³	

Thermal Properties	Metric	English	Comments
CTE, linear	7.20 $\mu\text{m}/\text{m}\cdot\text{°C}$	4.00 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 30.0 - 150 °C	@Temperature 86.0 - 302 °F	
	7.50 $\mu\text{m}/\text{m}\cdot\text{°C}$	4.17 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 30.0 - 400 °C	@Temperature 86.0 - 752 °F	
	7.90 $\mu\text{m}/\text{m}\cdot\text{°C}$	4.39 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 30.0 - 800 °C	@Temperature 86.0 - 1470 °F	
Thermal Conductivity	175 W/m-K	1210 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	20 %	20 %	
Molybdenum, Mo	80 %	80 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China