

## Ametek Ultra 304L P/M Stainless Steel, Sintered from 6.2 g/cc Green Density

Category: Metal, Ferrous Metal, Stainless Steel, T 300 Series Stainless Steel

## **Material Notes:**

Ametek's patented Ultra Stainless Steels™ are produced by alloying the conventional austenitic compositions with a small amount of a copper-nickel-tin alloy. This results in a marked improvement in corrosion resistance, while other properties are comparable to the conventional counterparts. Mechanical property data below is from samples lubricated with 1% Acrawax C and pressed at 30 tsi. Green strength 500 ksi. Specimens were delubricated in air for 20 min. at 950°F (510°C), then sintered in dissociated ammonia for 30 min. at 2100°F (1149°C) and cooled in the water jacketed furnace cooling zone. Dimensional change from die size -0.26%. Information provided by Ametek Specialty Metal Products.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Ametek-Ultra-304L-PM-Stainless-Steel-Sintered-from-62-gcc-Green-Density.php

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 6.18 g/cc | 0.223 lb/in <sup>3</sup> |          |

| Mechanical Properties      | Metric  | English   | Comments |
|----------------------------|---------|-----------|----------|
| Hardness, Rockwell B       | 37      | 37        |          |
| Tensile Strength, Ultimate | 250 MPa | 36300 psi |          |
| Tensile Strength, Yield    | 190 MPa | 27600 psi |          |
| Elongation at Break        | 4.1 %   | 4.1 %     |          |

| Component Elements Properties | Metric  | English | Comments   |
|-------------------------------|---------|---------|------------|
| Carbon, C                     | 0.020 % | 0.020 % |            |
| Chromium, Cr                  | 19 %    | 19 %    |            |
| Copper, Cu                    | 0.80 %  | 0.80 %  |            |
| Iron, Fe                      | 66 %    | 66 %    | as balance |
| Manganese, Mn                 | 0.20 %  | 0.20 %  |            |
| Nickel, Ni                    | 11 %    | 11 %    |            |
| Phosphorous, P                | 0.010 % | 0.010 % |            |
| Silicon, Si                   | 0.80 %  | 0.80 %  |            |
| Sulfur, S                     | 0.010 % | 0.010 % |            |
| Tin, Sn                       | 2.0 %   | 2.0 %   |            |



## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China