

ArcelorMittal IF 220 High strength IF steel, Cold rolled

Category : Metal , Ferrous Metal , Alloy Steel

Material Notes:

Available in the following: uncoated (HC220Y), electroglavanized (HC220Y+ZE) and Extragal®/Galvannealed

(HX220YD+Z/+ZF)Description: These steels were designed to provide an excellent combination of drawability and mechanical strength based on their specific interstitial free (IF) metallurgy. IF180 offers drawability similar to that of ArcelorMittal 04 combined with tensile strength comparable to that of H220, for example. These steels are hardened by adding manganese, silicon and phosphorous in solid solution to the ferrite. The metallurgy of IF steels optimizes their drawability. Their low YS/UTS ratio and high strain hardening coefficient ensure excellent deep-drawability and good strain redistribution. Their high strain ratio r ensures good deformation behavior, making them suitable for deep-drawing. These steels are particularly suitable for complex parts requiring high mechanical strength, such as wheel arches, toe-boards, reinforcements, etc. These steels have high strain hardening potential during forming, lending deep-drawn parts (trunks, tailgates, doors, linings, wheel arches, etc.) good dent resistance. The IF180 to IF 260 grades can be used, with certain coatings, to manufacture visible parts such as door panels. The IF 300 grade is designed for more complex structural parts (longitudinal beams, cross members, suspension and chassis components, etc.). Application: With their high mechanical strength guaranteeing good fatigue and impact resistance, these steels are intended for structural parts (longitudinal beams, cross members, B-pillars, etc.) as well as for skin parts, in which they provide good indentation resistance. In contrast to that of conventional drawing qualities, the weight reduction potential of these products increases with drawing depth. Information provided by ArcelorMittal

Order this product through the following link:

http://www.lookpolymers.com/polymer_ArcelorMittal-IF-220-High-strength-IF-steel-Cold-rolled.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	340 - 400 MPa	49300 - 58000 psi	
Tensile Strength, Yield	220 - 260 MPa	31900 - 37700 psi	
Elongation at Break	$\geq 33 \%$	$\geq 33 \%$	$L_{\geq 80 \text{ mm}}, t_{\leq 3 \text{ mm}}$
Fatigue Strength	$\leq 275 \text{ MPa}$	$\leq 39900 \text{ psi}$	
	@# of Cycles 2.00×10^6	@# of Cycles 2.00×10^6	
	$\leq 275 \text{ MPa}$	$\leq 39900 \text{ psi}$	
	@# of Cycles 1.00×10^7	@# of Cycles 1.00×10^7	
	$\leq 290 \text{ MPa}$	$\leq 42100 \text{ psi}$	
	@# of Cycles 100000	@# of Cycles 100000	

Component Elements Properties	Metric	English	Comments
Carbon, C	$\leq 0.010 \%$	$\leq 0.010 \%$	
Iron, Fe	$\geq 98.79 \%$	$\geq 98.79 \%$	as balance
Manganese, Mn	$\leq 0.70 \%$	$\leq 0.70 \%$	

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China