

ArcelorMittal Save 27-17 Electrical Steel

Category : Metal , Ferrous Metal , Alloy Steel

Material Notes:

Properties: The iCARE™ Save product family comes with guaranteed losses at 400Hz and indicative maximum values at 700Hz. These values are representative of the steel's behaviour at high frequencies. **Advantages:** Save grades enable you to reduce the iron losses from the stators of synchronous machines. They are particularly useful for reducing iron losses in high-speed hybrid and electric traction machines, and generators which extend the range of electric vehicles. **Applications:** Save grades are most effective at reducing iron losses from machine parts which are subject to high base frequencies and additional harmonics. Save thus helps to improve machine efficiency, which leads to an increase in power density. Power density can be tuned to create a lighter, smaller machine, or a more powerful machine for a given weight. Driving range is extended as Save reduces machine weight and costs and saves battery energy. **Recommendations for use:** Save grades can be used immediately after lamination punching. The punching effect can be eliminated by performing a stress relief annealing. This optimises their performance in applications with fine teeth, and enables a substantial part of the lower frequency area to be exploited. A C5-type coating is recommended. Save stacks can be produced using existing assembly techniques such as interlocking or welding. Information provided by ArcelorMittal

Order this product through the following link:

http://www.lookpolymers.com/polymer_ArcelorMittal-Save-27-17-Electrical-Steel.php

Physical Properties	Metric	English	Comments
Density	7.60 g/cc	0.275 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	195 - 225	195 - 225	L direction
	195 - 225	195 - 225	T direction
Tensile Strength, Ultimate	510 - 550 MPa	74000 - 79800 psi	L direction
	540 - 580 MPa	78300 - 84100 psi	T direction
Tensile Strength, Yield	390 - 430 MPa	56600 - 62400 psi	L direction
	410 - 450 MPa	59500 - 65300 psi	T direction
Elongation at Break	15 - 30 %	15 - 30 %	L direction
	15 - 30 %	15 - 30 %	T direction

Magnetic Properties	Metric	English	Comments
Core Loss	<= 17.0 W/kg	<= 7.71 W/lb	at 1T, Guaranteed
	@Frequency 400 Hz	@Frequency 400 Hz	
	<= 40.0 W/kg	<= 18.1 W/lb	at 1T, Indicative

Magnetic Properties	@Frequency 700 Hz Metric	@Frequency 700 Hz English	Comments
Descriptive Properties	Value		Comments
Anisotropy	>15%		400 Hz at 1T
Polarization	>1.49 T		at 2,500 A/m
	>1.6 T		at 5,000 A/m
	>1.7 T		at 10,000 A/m

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China