

Aremco Aremco-Seal™ 613 High Temperature Specialty Coatings Glass

Category : Ceramic , Glass

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aremco-Aremco-Seal-613-High-Temperature-Specialty-Coatings-Glass.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	
Solids Content	54 %	54 %	by weight
Volatile Organic Compounds (VOC) Content	0.00 g/l	0.00 g/l	
Viscosity	1000 - 2000 cP	1000 - 2000 cP	
Storage Temperature	4.44 - 32.2 °C	40.0 - 90.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	621 °C	1150 °F	Continuous

Processing Properties	Metric	English	Comments
Processing Temperature	10.0 - 32.2 °C	50.0 - 90.0 °F	Application Temperature
Dry Time	0.5 hour	0.5 hour	Touch
	0.5 hour	0.5 hour	Handling
	0.5 - 1 hour	0.5 - 1 hour	Recoat
Cure Time	30.0 - 60.0 min	0.500 - 1.00 hour	Air Set prior to curing
	30.0 min	0.500 hour	
	@Temperature 621 °C	@Temperature 1150 °F	
Shelf Life	6.00 Month	6.00 Month	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China