

## Aremco Ceramacast™ 675 High Temperature Potting & Casting Material Aluminum Nitride

Category : Ceramic , Nitride , Potting/Casting Ceramic

### Material Notes:

Fine grain aluminum nitride castable with high thermal conductivity

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aremco-Ceramacast-675-High-Temperature-Potting-Casting-Material-Aluminum-Nitride.php](http://www.lookpolymers.com/polymer_Aremco-Ceramacast-675-High-Temperature-Potting-Casting-Material-Aluminum-Nitride.php)

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in <sup>3</sup>	
Porosity	<= 3.0 %	<= 3.0 %	
Viscosity	12000 cP	12000 cP	
Thickness	12.7 microns	0.500 mil	0

Mechanical Properties	Metric	English	Comments
Compressive Strength	13.8 MPa	2000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	5.22 $\mu\text{m}/\text{m}\cdot\text{°C}$	2.90 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Maximum Service Temperature, Air	1200 °C	2200 °F	
Shrinkage	<= 0.300 %	<= 0.300 %	
	@Temperature 538 °C	@Temperature 1000 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	
Dielectric Strength	11.8 kV/mm	300 kV/in	

Processing Properties	Metric	English	Comments
Dry Time	>= 8 hour	>= 8 hour	Air dry
Cure Time	300 - 420 min	5.00 - 7.00 hour	2-4 hrs at 200°F; 3 hrs at 250°F
Pot Life	60 - 120 min	60 - 120 min	
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Acid Resistance	Good	attacked by HF
Alkali Resistance	Good	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China