

## Aremco Ceramacoat™ 845-GRY High Temperature Ceramic-Inorganic Coating

Category : Ceramic , Other Engineering Material , Ceramic/Metallic Coating

### Material Notes:

Single part, waterborne, silicon-filled, phosphate-bonded, gray coating for glass and quartz to 2000 °F (1093 °C). Primarily used for marking ceramic parts and coating automotive headlamps, stadium lighting and quartz vessels for the semiconductor industry. Standard viscosity is 200–400 cP; a higher viscosity coating, 845-HV, in the range of 500–800 cP is available upon request.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aremco-Ceramacoat-845-GRY-High-Temperature-Ceramic-Inorganic-Coating.php](http://www.lookpolymers.com/polymer_Aremco-Ceramacoat-845-GRY-High-Temperature-Ceramic-Inorganic-Coating.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.65 g/cc	1.65 g/cc	
Solids Content	25.2 %	25.2 %	by volume
	51.8 %	51.8 %	by weight
Volatile Organic Compounds (VOC) Content	0.00 g/l	0.00 g/l	
Viscosity	400 - 700 cP	400 - 700 cP	
Thickness	25.4 microns	1.00 mil	recommended dry film thickness
	101 microns	3.97 mil	estimated wet film thickness
Storage Temperature	12.8 - 29.4 °C	55.0 - 85.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	816 °C	1500 °F	Continuous

Processing Properties	Metric	English	Comments
Processing Temperature	10.0 - 32.2 °C	50.0 - 90.0 °F	Application Temperature
Cure Time	5.00 min	0.0833 hour	Step 2
	@Temperature 482 °C	@Temperature 900 °F	
Shelf Life	10.0 min	0.167 hour	Step 1, preceeded by >10 min. air set
	@Temperature 93.3 °C	@Temperature 200 °F	

Descriptive Properties	Value	Comments
Color	Gray	Cured

Dry Film Coverage ft <sup>2</sup> /gal Descriptive Properties	404 Value	at 1 mil Comments
Thinner	845-T	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China