

## Aremco Corr-Paint™ CP4050-S High Temperature Protective Coating Silicone-Polyester

Category : Other Engineering Material , Ceramic/Metallic Coating , Polymer , Thermoset , Silicone

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aremco-Corr-Paint-CP4050-S-High-Temperature-Protective-Coating-Silicone-Polyester.php](http://www.lookpolymers.com/polymer_Aremco-Corr-Paint-CP4050-S-High-Temperature-Protective-Coating-Silicone-Polyester.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.46 g/cc	1.46 g/cc	
Solids Content	57.4 %	57.4 %	by weight
	62.1 %	62.1 %	by volume
Volatile Organic Compounds (VOC) Content	443 g/l	443 g/l	
Viscosity	250 - 350 cP	250 - 350 cP	
Thickness	25.4 microns	1.00 mil	recommended dry film thickness
	44.2 microns	1.74 mil	estimated wet film thickness
Storage Temperature	4.44 - 32.2 °C	40.0 - 90.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	316 °C	600 °F	Continuous
	427 °C	800 °F	Intermittent
Flash Point	46.1 °C	115 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	10.0 - 48.9 °C	50.0 - 120 °F	Application Temperature
Dry Time	1.00 - 2.00 hour	1.00 - 2.00 hour	Touch
	2.00 - 4.00 hour	2.00 - 4.00 hour	Handling
	1.0 - 24.0 hour	1.0 - 24.0 hour	Recoat
Cure Time	>= 60.0 min	>= 1.00 hour	Air Set prior to curing
	45.0 min @Temperature 249 °C	0.750 hour @Temperature 480 °F	
			Adequate ventilation is required when

Processing Properties	Metric <sup>EN</sup>	English <sup>US</sup>	Comments
	@Temperature 232 °C	@Temperature 450 °F	curing these products. Outgassing will occur above 300°F and cease after 750°F. An additional 30 minutes is required at the highest service temperature if service temperature is below 750°F.
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Color	Green	
Dry Film Coverage ft <sup>2</sup> /gal	920.3	at 1 mil
Primer	Not Required	
Thinner	PM Acetate	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China