

Aremco Pyro-Putty™ 1000 High Temperature Ceramic-Metallic Putty, Aluminum Filled

Category : Ceramic , High Temp Ceramic Resin

Material Notes:

Ceramic and Aluminum-Filled, Two-Part, Water Based Paste.For Applications to 1/2" Thick.Repairs Cast Aluminum Parts to 1400°F

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aremco-Pyro-Putty-1000-High-Temperature-Ceramic-Metallic-Putty-Aluminum-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.80 g/cc	1.80 g/cc	
Storage Temperature	4.44 - 32.2 °C	40.0 - 90.0 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	760 °C	1400 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 120 min	1.00 - 2.00 hour	2-4 hrs Air Set; 1-2 hrs at 160°F
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Color	Light Gray	
Filler	Aluminum	
Mix Ratio	2:1	powder:liquid

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China