

Arkema Group EVATANE® 33-25 Copolymer Ethylene - Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Adhesive/Sealant Grade

Material Notes:

EVATANE® 33-25 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerisation process.

EVATANE® 33-25 is stabilized with antioxidants. The High Vinyl Acetate content of EVATANE® 33-25 brings softness, flexibility and polarity. EVATANE® 33-25 is compatible with tackifying resins and waxes. It's a useful product for hot melt adhesives formulation.

EVATANE® 33-25 delivers high cohesive strength with any kind of fillers (HFFR compounds, sound dampening). Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-EVATANE-33-25-Copolymer-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc @Temperature 23.0 °C	0.0347 lb/in ³ @Temperature 73.4 °F	ISO 1183
Vinyl Acetate Content	32 - 34 %	32 - 34 %	FTIR (internal)
Melt Index of Compound	22 - 29 g/10 min @Load 2.16 kg, Temperature 190 °C	22 - 29 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	67	67	ASTM D2240
Tensile Strength at Break	11.0 MPa	1600 psi	ASTM D638
Elongation at Break	900 - 1100 %	900 - 1100 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	63.0 °C	145 °F	DSC
Vicat Softening Point	<= 40.0 °C @Load 0.999 kg	<= 104 °F @Load 2.20 lb	ISO 306
Ring & Ball Softening Point	119 °C	246 °F	ASTM E28

Processing Properties	Metric	English	Comments
Processing Temperature	<= 230 °C	<= 446 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China