

Arkema Group Evatane® 1003 VL 4S Ethylene Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

EVA copolymer made by high pressure tubular process. Anti-UV stabilized grade. Applications Grade for transparent and thermal agricultural film to 180 at 200 µ for greenhouse coverage. ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Evatane-1003-VL-4S-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in ³	
Melt Flow	0.45 g/10 min @Load 2.16 kg, Temperature 190 °C	0.45 g/10 min @Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	6.00 MPa	870 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Tensile Modulus	0.0500 GPa	7.25 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	93.0 °C	199 °F	10°C/min
Vicat Softening Point	73.0 °C	163 °F	50°C/hr; 50N

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Mfr. reports 'Transparent' but doesn't quantify.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China