

Arkema Group KYNAR® EXAD 3000 Polyvinylidene Fluoride - Extrusion

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

Material Notes:

Characteristics: Natural resin - translucent, off-white hemispheres. Extrusion aid, lubricated. High stability in harsh thermal, chemical and ultraviolet environments. High toughness and mechanical strength, low permeability, abrasion resistance; high purity
Applications: Chemical processing – production, storage and transfer of corrosive fluids
Electronics – protective sheathing, plenum and wiring insulation
Semi-conductor industry
Food stuff and Healthcare industries
Transportation – fuel line and pipe, thermoformed body components
Information provided by Arkema Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-KYNAR-EXAD-3000-Polyvinylidene-Fluoride-Extrusion.php

Physical Properties	Metric	English	Comments
Bulk Density	0.961 g/cc	0.0347 lb/in ³	
Viscosity	1.20e+6 - 1.80e+6 cP @Shear Rate 100 1/s, Temperature 232 °C	1.20e+6 - 1.80e+6 cP @Shear Rate 100 1/s, Temperature 450 °F	Melt Viscosity; ASTM D3835
Melt Flow	2.0 - 7.0 g/10 min @Load 5.00 kg, Temperature 232 °C	2.0 - 7.0 g/10 min @Load 11.0 lb, Temperature 450 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	140 - 145 °C	284 - 293 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China