

Arkema Group LOTADER® 6200 Terpolymer Ethylene - Acrylic Ester - Maleic Anhydride

Category : Polymer , Thermoplastic , EMAAA Terpolymer

Material Notes:

LOTADER 6200 is a random terpolymer of Ethylene, Acrylic Ester and Maleic Anhydride, polymerized under high pressure in an autoclave process. Due to its properties (reactivity, fluidity), LOTADER 6200 is an additive of choice for hot melt adhesives formulation. It is also use as a coupling agent in mineral filled compounds. Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-LOTADER-6200-Terpolymer-Ethylene-Acrylic-Ester-Maleic-Anhydride.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ISO 1183
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Melt Index of Compound	40 g/10 min	40 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	36	36	ASTM D2240
Tensile Strength at Break	10.0 MPa	1450 psi	ASTM D638
Elongation at Break	600 %	600 %	ASTM D638
Flexural Modulus	0.0950 GPa	13.8 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	102 °C	216 °F	DSC
Vicat Softening Point	70.0 °C	158 °F	ASTM D1525
	@Load 0.999 kg	@Load 2.20 lb	
Ring & Ball Softening Point	119 °C	246 °F	ASTM E28

Chemical Properties	Metric	English	Comments
Acid Value	17	17	mg KOH/g; Titration

Processing Properties	Metric	English	Comments
Processing Temperature	<= 300 °C	<= 572 °F	

Descriptive Properties	Value	Comments
Ethyl Acrylate Content (%)	6.5	IRTF (internal)
Maleic Anhydride Content (%)	2.8	IRTF (internal)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China