

Arkema Group LOTRYL® 28 MA 07 Copolymer Ethylene - Methyl Acrylate

Category : Polymer , Thermoplastic , Ethylene Methyl Acrylate

Material Notes:

LOTRYL® 28 MA 07 is a random copolymer of ethylene and methyl acrylate made by high-pressure radical polymerisation process. Due to the high methyl acrylate content, LOTRYL® 28 MA 07 is a polymer of choice for applications where softness, flexibility and polarity are required. Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-LOTRYL-28-MA-07-Copolymer-Ethylene-Methyl-Acrylate.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc @Temperature 23.0 °C	0.0343 lb/in ³ @Temperature 73.4 °F	ISO 1183
Methyl Acrylate Content	26 - 30 %	26 - 30 %	IRTF (internal)
Melt Index of Compound	6.0 - 8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	6.0 - 8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	76	76	ASTM D2240
Tensile Strength at Break	7.00 MPa	1020 psi	ASTM D638
Elongation at Break	900 %	900 %	ASTM D638
Flexural Modulus	0.0100 GPa	1.45 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	65.0 °C	149 °F	DSC
Vicat Softening Point	<= 40.0 °C @Load 1.02 kg	<= 104 °F @Load 2.25 lb	ASTM D1525
Ring & Ball Softening Point	150 °C	302 °F	ASTM E28

Processing Properties	Metric	English	Comments
Processing Temperature	<= 300 °C	<= 572 °F	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China