

## Arkema Group OREVAC® 18390 Maleic Anhydride Modified Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , Anhydride-Modified Polyethylene

### Material Notes:

OREVAC® 18390 is anhydride modified polyethylene. It is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins. OREVAC® 18390 provides outstanding adhesion to PE, PA, EVOH, PETG, APET. It is typically used as tie-layer in multilayer structures. It is used in flexible packaging, thermoformed containers or blow-molded bottles. Information provided by Arkema Group

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arkema-Group-OREVAC-18390-Maleic-Anhydride-Modified-Polyethylene.php](http://www.lookpolymers.com/polymer_Arkema-Group-OREVAC-18390-Maleic-Anhydride-Modified-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.885 g/cc @Temperature 23.0 °C	0.0320 lb/in <sup>3</sup> @Temperature 73.4 °F	ISO 1183
Melt Index of Compound	5.0 g/10 min @Load 2.16 kg, Temperature 190 °C	5.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	75.0 °C	167 °F	DSC
Vicat Softening Point	52.0 °C	126 °F	ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China