

Arkema Group OREVAC® 18722 Maleic Anhydride Modified Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

OREVAC 18722 is a maleic anhydride modified PP based resin. It is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyolefins. OREVAC 18722 is an extrusion adhesive to be used in coextrusion technologies. As adhesive, OREVAC 18722 has been designed to develop adhesion in coextrusion between PP and EVOH or PP and PA .Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-OREVAC-18722-Maleic-Anhydride-Modified-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ISO 1183
Melt Index of Compound	7.0 - 9.0 g/10 min @Load 2.16 kg, Temperature 230 °C	7.0 - 9.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	143 °C	289 °F	DSC
Vicat Softening Point	115 °C	239 °F	ISO 306

Processing Properties	Metric	English	Comments
Feed Temperature	240 °C	464 °F	
Adapter Temperature	230 °C	446 °F	
Die Temperature	240 °C	464 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China