

Arkema Group OREVAC® 9309 EVA Terpolymer

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

OREVAC® is a range of ethylene-vinyl acetate copolymers modified by adjunction of polar groups which, when molten, have excellent adhesive properties to various substrates. They are supplied as free flowing natural coloured granules. Applications include blown film extrusion, cast film coextrusion, and thermo-adhesive films. Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-OREVAC-9309-EVA-Terpolymer.php

Physical Properties	Metric	English	Comments
Density	0.932 g/cc	0.0337 lb/in ³	ASTM D1505
Vinyl Acetate Content	8.0 - 9.5 %	8.0 - 9.5 %	Arkema
Melt Index of Compound	3.3 - 4.7 g/10 min @Load 2.16 kg, Temperature 190 °C	3.3 - 4.7 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91	91	ASTM D2240
Tensile Strength at Break	18.0 MPa	2610 psi	ASTM D638
	22.0 MPa	3190 psi	Film Property, 50 µm thickness; ASTM D882
Tensile Strength, Yield	6.00 MPa	870 psi	ASTM D638
	6.00 MPa	870 psi	Film Property, 50 µm thickness; ASTM D882
Elongation at Break	500 - 700 %	500 - 700 %	Film Property, 50 µm thickness; ASTM D882
	600 - 900 %	600 - 900 %	ASTM D638
Dart Drop Test	355 g	0.783 lb	ASTM D1709

Thermal Properties	Metric	English	Comments
Melting Point	105 °C	221 °F	DSC
Vicat Softening Point	79.0 °C	174 °F	ASTM D1525
Ring & Ball Softening Point	182 °C	360 °F	

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Descriptive Properties	Value	Comments
------------------------	-------	----------

MAH Mini	1600	
----------	------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China