

Arkema Group Orevac® 18303S Maleic Anhydride modified LLDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

LLDPE base Composition: PE / Adh./ EVOH Applications:Flooring Heating TubeInformation provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Orevac-18303S-Maleic-Anhydride-modified-LLDPE.php

Physical Properties	Metric	English	Comments
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	

Thermal Properties	Metric	English	Comments
Melting Point	124 °C	255 °F	
Vicat Softening Point	93.0 °C	199 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China