

## Arkema Group Orevac® 18732 RBP Maleic Anhydride modified Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

PP base Structure: Repairing and joint Applications: Pipe Coating Information provided by Arkema Group

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arkema-Group-Orevac-18732-RBP-Maleic-Anhydride-modified-Polypropylene.php](http://www.lookpolymers.com/polymer_Arkema-Group-Orevac-18732-RBP-Maleic-Anhydride-modified-Polypropylene.php)

Physical Properties	Metric	English	Comments
Melt Flow	8.0 g/10 min	8.0 g/10 min	
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Thermal Properties	Metric	English	Comments
Melting Point	161 °C	322 °F	
Vicat Softening Point	120 °C	248 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China