

## Arkema Group Orgalloy® P 60AD Nylon (Conditioned)

Category : Polymer , Thermoplastic , Nylon

**Material Notes:**

ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arkema-Group-Orgalloy-P-60AD-Nylon-Conditioned.php](http://www.lookpolymers.com/polymer_Arkema-Group-Orgalloy-P-60AD-Nylon-Conditioned.php)

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in <sup>3</sup>	
Melt Flow	0.50 g/10 min @Load 2.16 kg, Temperature 235 °C	0.50 g/10 min @Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	210 °C	410 °F	10°C/min
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China