

Arkema Group Rilsan® AMN P40 TLD Nylon 12, Flexible, Injection Grade (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Designation ISO 1874-PA12-P,MHLR,14-004Flexible grade for injection molding. Available colors: black and natural. Light and heat stabilized. Mold-release agent.Good impact strength. Flexibility and dynamic properties even at low temperatures. Easy filling of the mold due to its well adapted viscosity. Low shrinkage: include 1% on average for the design of the mold. Good dimensional stability (low moisture absorption).Example applications: Flexible parts with high impact strength and vibration resistance.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-AMN-P40-TLD-Nylon-12-Flexible-Injection-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	1.2 %	1.2 %	
Melt Flow	48.8 g/10 min	48.8 g/10 min	
	@Load 2.16 kg, Temperature 235 °C	@Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.0 MPa	3770 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	26 %	26 %	50 mm/min
Tensile Modulus	0.440 GPa	63.8 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	168 °C	334 °F	10°C/min
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.10 mm	@Thickness 0.122 in	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.00036	0.00036	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Electrical Properties	0.00123 Metric	0.00123 English	Comments
	@Frequency 100 Hz	@Frequency 100 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China