

Arkema Group Rilsan® ASR 30 Nylon 12, 30% Carbon Fiber Filled (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, Carbon Fiber Filled

Material Notes:

Designation ISO 1874-PA12,M,16-120,CF30Rigid grade with carbon fiber filler (30%) for injection molding. Available color: black.Very high rigidity. High strength-to-weight ratio. Very low shrinkage: include 0,5% on average for the design of the mold. High dimensional stability (low moisture absorption). Antistatic properties.Example applications: Parts with high mechanical properties and dimensional precision.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-ASR-30-Nylon-12-30-Carbon-Fiber-Filled-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	
Melt Flow	3.0 g/10 min	3.0 g/10 min	
	@Load 2.16 kg, Temperature 235 °C	@Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	154 MPa	22300 psi	5 mm/min
Elongation at Break	3.0 %	3.0 %	5 mm/min
Tensile Modulus	14.0 GPa	2030 ksi	1 mm/min
Charpy Impact Unnotched	5.92 J/cm ²	28.2 ft-lb/in ²	
	5.86 J/cm ² @Temperature -30.0 °C	27.9 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.55 J/cm ²	7.38 ft-lb/in ²	
	0.910 J/cm ² @Temperature -30.0 °C	4.33 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C	22.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	174 °C	345 °F	(Dry)
Deflection Temperature at 0.46 MPa (66 psi)	175 °C	347 °F	
Deflection Temperature at 1.8 MPa (264 psi)	162 °C	324 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	170 °C	338 °F	50°C/67; 50N
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.10 mm	@Thickness 0.122 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	400 ohm-cm	400 ohm-cm	
Dielectric Strength	1.00 kV/mm	25.4 kV/in	
Comparative Tracking Index	100 V	100 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China