

Arkema Group Rilsan® MA 4411 Nylon 12, Flexible Tubing Grade (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, Extrusion/Tubing Grade

Material Notes:

Designation ISO 1874-PA12-HI,EHL,22-003Flexible grade for tubes extrusion. Available colors: black and natural. Light and heat stabilized.Flexibility. High burst pressure and impact strength. Fit for use in a wide range of temperature. Very good chemical resistance.Example applications: Fuel line.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-MA-4411-Nylon-12-Flexible-Tubing-Grade-Dry.php

Physical Properties	Metric	English	Comments
Water Absorption	1.2 %	1.2 %	
Moisture Absorption at Equilibrium	0.65 %	0.65 %	Humidity Absorption
Melt Flow	4.9 g/10 min @Load 2.16 kg, Temperature 235 °C	4.9 g/10 min @Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.0 MPa	4210 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	23 %	23 %	50 mm/min
Tensile Modulus	0.555 GPa	80.5 ksi	1 mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	Low Temp
Charpy Impact, Notched	0.410 J/cm ² @Temperature -30.0 °C	1.95 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	41.0 °C	106 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China