

Arkema Group Rilsan® MB 3501 Nylon 11, Flexible Tubing Grade (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 11 , Nylon 11, Flexible Tubing Grade

Material Notes:

Designation ISO 1874-PA11-HI,MHL,22-004Flexible grade for tubes extrusion. Available color: black. Light and heat stabilized.Flexibility. High burst pressure and impact strength. Fit for use in a wide range of temperature. Good chemical resistance.Example applications: Tubes for air brake system. approved by ISO 7628, DIN 73378 (PA11-PHLY), NFR 12632, SAEJ 844.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Rilsan-MB-3501-Nylon-11-Flexible-Tubing-Grade-Conditioned.php

Physical Properties	Metric	English	Comments
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 235 °C	1.0 g/10 min @Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.0 MPa	4640 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	33 %	33 %	50 mm/min
Tensile Modulus	0.575 GPa	83.4 ksi	1 mm/min
Charpy Impact Unnotched	NB	NB	
	NB	NB	Low Temp
Charpy Impact, Notched	NB	NB	
	1.02 J/cm ² @Temperature -30.0 °C	4.85 ft-lb/in ² @Temperature -22.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China