

Arlon 0.008" (0.2032 mm) Flexible Heater Silicone with Fiberglass Substrate (44571R008)

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Silicone

Material Notes:

0.0015 in. (0.038 mm) minimum Cured silicone rubber/Prime Coated 7628 Fiberglass/ 0.0015 in (0.038 mm) minimum uncured silicone rubber; 0.0015 in. (0.038 mm) polyethylene interleave; overall thickness 0.008 in. + 0.001, -0.0005 (0.2 mm +0.02, -0.01). The shelf life is defined as the duration of time for which the product will meet the physical requirements outlined below. It does not guarantee the product's usefulness in all applications. Color: Red. Weight: 281.4 g/m² ± 30.52 (8.3 oz./yd.² ± 0.9). Shelf Life: 6 months from date of manufacture at 23.8°C (75°F). Cure Time: 0.25 hours. Post Cure: 204°C (400°F), for 2 hours. Information provided by the manufacturer, Arlon Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-0008-02032-mm-Flexible-Heater-Silicone-with-Fiberglass-Substrate-44571R008.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	
Tensile Strength, Ultimate	5.58 - 6.82 MPa	809 - 989 psi	
Elongation at Yield	540 - 660 %	540 - 660 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	Mechanical per UL Card E54153
	232 °C	450 °F	
Minimum Service Temperature, Air	-56.6 °C	-69.9 °F	
UL RTI, Electrical	220 °C	428 °F	per UL Card E54153
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.75 kV/mm	>= 400.0 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	176.6 °C	349.9 °F	curing temp., at 0.345 MPa (50 psi)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China