

## Arlon 0.015" (0.381 mm) Flexible Heater Silicone with Fiberglass Substrate (51941C015)

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Silicone

### Material Notes:

Uncured silicone rubber with a minimum thickness of 0.003 in. (0.08 mm)/0.008 in. (0.2 mm) Prime Coated 7628 Fiberglass/Uncured silicone rubber with a minimum thickness of 0.003 in. (0.08 mm); 0.003 in. (0.08 mm) polyethylene interleave; overall thickness 0.015 in  $\pm$  0.0015 (0.38 mm  $\pm$  0.038). The shelf life is defined as the duration of time for which the product will meet the physical requirements outlined below. It does not guarantee the product's usefulness in all applications. Color: Red. Weight: 569.6 g/m<sup>2</sup>  $\pm$  50.9 (16.8 oz./yd.<sup>2</sup>  $\pm$  1.5). Shelf Life: 6 months from date of manufacture at 23.8°C (75°F). Cure Time: 0.25 hours. Post Cure: 204°C (400°F), for 2 hours.Applications: Hose and duct materials.Information provided by the manufacturer, Arlon Silicone Technologies Division.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-0015-0381-mm-Flexible-Heater-Silicone-with-Fiberglass-Substrate-51941C015.php](http://www.lookpolymers.com/polymer_Arlon-0015-0381-mm-Flexible-Heater-Silicone-with-Fiberglass-Substrate-51941C015.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50 - 60	50 - 60	
Tensile Strength, Ultimate	$\geq$ 6.90 MPa	$\geq$ 1000 psi	
Elongation at Break	$\geq$ 450 %	$\geq$ 450 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.6 °C	-69.9 °F	
Flammability, UL94	V-0	V-0	UL Card E109181

Electrical Properties	Metric	English	Comments
Dielectric Strength	$\geq$ 15.75 kV/mm	$\geq$ 400.0 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	176.6 °C	349.9 °F	curing temp.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China