

Arlon 10502N060 0.060" (1.52 mm) Cured/Post-Cured Unsupported Silicone Rubber

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

Design/Construction:Side 1: Cured/Post-Cured Unsupported Silicone Rubber Appearance: Red silicone rubber This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-10502N060-0060-152-mm-CuredPost-Cured-Unsupported-Silicone-Rubber.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene Interleave
	1370 - 1680 microns	54.0 - 66.0 mil	Overall
	1370 - 1680 microns	54.0 - 66.0 mil	Side 1

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50 - 60	50 - 60	Compound Property
Tensile Strength	7.45 - 9.10 MPa	1080 - 1320 psi	Compound Property
Elongation at Break	540 - 660 %	540 - 660 %	Compound Property
100% Modulus	>= 0.00172 GPa	>= 0.250 ksi	Compound Property
Tear Strength	>= 43.8 kN/m	>= 250 pli	Compound Property
Compression Set	<= 28 %	<= 28 %	After Post Cure, Compound Property

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	Compound Property

Descriptive Properties	Value	Comments
Color	Translucent	
Total Product Weight (oz/yd2)	62.1 - 75.9	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China