

## Arlon 10842S125 Cured/Post-cured, Unsupported Silicone Rubber

Category : Polymer , Thermoset , Silicone , Silicone Rubber

### Material Notes:

Low Modulus Product Color: Saddle Brown Interleave: 0.003" Polyethylene This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-10842S125-CuredPost-cured-Unsupported-Silicone-Rubber.php](http://www.lookpolymers.com/polymer_Arlon-10842S125-CuredPost-cured-Unsupported-Silicone-Rubber.php)

Physical Properties	Metric	English	Comments
Thickness	3180 microns	125 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	35 - 45	35 - 45	
Tensile Strength	>= 6.89 MPa	>= 1000 psi	
Elongation at Break	>= 700 %	>= 700 %	
100% Modulus	0.00103 GPa	0.150 ksi	
Tear Strength	>= 35.1 kN/m	>= 200 pli	
Compression Set	<= 28 %	<= 28 %	After post cure

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Total Product Weight (oz/yd2)	105	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China