

Arlon 31970XA015 Silicone Rubber Laminate

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

The interleave is 3 mil of polyethylene, side 1 is uncured silicone rubber and the carrier is HDPE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-31970XA015-Silicone-Rubber-Laminate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.44 g/cc	1.44 g/cc	Silicone Property; Arlon SQA-TMS-024
Thickness	178 microns	7.00 mil	carrier; Arlon SQA-TMS-003
	381 microns	15.0 mil	overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	62	62	Silicone Property; ASTM D2240
Tensile Strength, Ultimate	8.89 MPa	1290 psi	Silicone Property; ASTM D412
Elongation at Break	150 %	150 %	Silicone Property; ASTM D412
Tear Strength	14.5 kN/m	83.0 pli	Silicone Property; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	V-1	V-1	

Electrical Properties	Metric	English	Comments
Dielectric Strength	38.5 kV/mm	977 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Gray	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China