

## Arlon 32580R035 0.035" (0.889 mm) Uncured Silicone Rubber on PET Carrier

Category : Polymer , Thermoset , Silicone , Silicone Rubber

### Material Notes:

Design/Construction: Interleave: PolyethyleneSide 1: Uncured Silicone RubberCarrier: PETAppearance: Red silicone gum on polymer linerThis data represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-32580R035-0035-0889-mm-Uncured-Silicone-Rubber-on-PET-Carrier.php](http://www.lookpolymers.com/polymer_Arlon-32580R035-0035-0889-mm-Uncured-Silicone-Rubber-on-PET-Carrier.php)

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in <sup>3</sup>	Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Interleave
	127 microns	5.00 mil	Carrier; Arlon SQA-TMS-003
	889 microns	35.0 mil	Overall; Arlon SQA-TMS-003
	889 microns	35.0 mil	Side 1; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	37	37	Silicone Property; ASTM D2240
Tensile Strength	6.55 MPa	950 psi	Silicone Property; ASTM D412
Elongation at Break	620 %	620 %	Silicone Property; ASTM D412
Tear Strength	26.3 kN/m	150 pli	Die B, Silicone Property; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	200 °C	392 °F	E54153
UL RTI, Mechanical without Impact	200 °C	392 °F	E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	15.7 kV/mm	400 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	120 min Metric	2.00 hour English	Comments
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	Recommended Cure Cycle
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
	Translucent	Carrier
Total Product Weight (oz/yd2)	37	Arlon SQA-TMS-025

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China