

Arlon 41570R020 0.020" Uncured, Unsupported Silicone Rubber on Release Carrier

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

Design/Construction: Interleave: 0.003" Polyethylene Side 1: Uncured, Unsupported Silicone Rubber Substrate: Holland Cloth Carrier This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-41570R020-0020-Uncured-Unsupported-Silicone-Rubber-on-Release-Carrier.php

Physical Properties	Metric	English	Comments
Thickness	127 microns	5.00 mil	Substrate
	508 microns	20.0 mil	Silicone

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	Silicone Property
Tensile Strength	>= 5.52 MPa	>= 800 psi	Silicone Property
Elongation at Break	>= 500 %	>= 500 %	Silicone Property

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	220 °C	428 °F	E63753
UL RTI, Mechanical without Impact	200 °C	392 °F	E63753
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	Recommended Cure Cycle
	@Temperature 177 °C	@Temperature 350 °F	
	120 min	2.00 hour	Recommended Post Cure Cycle

Processing Properties	@Temperature 204 °C Metric	@Temperature 400 °F English	Comments
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	17.6	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China