

Arlon 43191R012 0.012" (0.305 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Uncured Silicone Rubber Side 2: Uncured Silicone Rubber Appearance: Red silicone gum on fiberglass cloth
This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-43191R012-0012-0305-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene Interleave
	76.2 - 102 microns	3.00 - 4.00 mil	Side 1
	76.2 - 102 microns	3.00 - 4.00 mil	Side 2
	102 microns	4.00 mil	Prime Coated 112 Fiberglass, Substrate
	279 - 330 microns	11.0 - 13.0 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45 - 55	45 - 55	Compound Property
Tensile Strength	>= 5.86 MPa	>= 850 psi	Compound Property
Elongation at Break	>= 350 %	>= 350 %	Compound Property
Peel Strength	>= 1.40 kN/m	>= 8.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability Test	<= 3.0	<= 3.0	[in], Char Length
	<= 25	<= 25	[sec], Flame and Glow Time; FTMS 191A, Method 5903

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
Shelf Life	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	10.3 - 12.3	
Uncoated Fabric Break Strength	80 lb/in	Fill Direction, Substrate Property
	90 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China