

Arlon 48362X005 0.005" (0.127 mm) Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Cured Silicone RubberSubstrate: Style 1080 FiberglassProduct Use: Flexible hose/duct substrateAppearance: Gray silicone rubber on fiberglass fabricThis data represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-48362X005-0005-0127-mm-Cured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	50.8 microns	2.00 mil	Side 1; Arlon SQA-TMS-003
	76.2 microns	3.00 mil	Substrate; Arlon SQA-TMS-003
	127 microns	5.00 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	Silicone Property; ASTM D2240
Tensile Strength	6.89 MPa	1000 psi	Silicone Property; ASTM D412
Elongation at Break	275 %	275 %	Silicone Property; ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability Test	0.00	0.00	[sec], After Flame Time
	0.50	0.50	[in], Flame Propagation

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Gray	

Descriptive Properties <small>Total Density Weight (oz/yd²)</small>	Value	Comments <small>Adm. Code: TMS-025</small>
--	-------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China