

Arlon 51576XC015A 0.015" (0.381 mm) Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: Polyethylene Side 1: Uncured Silicone Rubber Substrate: 7628 Style Fiberglass Side 2: Cured Silicone Rubber This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-51576XC015A-0015-0381-mm-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Interleave
	88.9 microns	3.50 mil	Side 1; Arlon SQA-TMS-003
	88.9 microns	3.50 mil	Side 2; Arlon SQA-TMS-003
	203 microns	8.00 mil	Substrate; Arlon SQA-TMS-003
	381 microns	15.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	Silicone Property; ASTM D2240
Tensile Strength	6.38 MPa	925 psi	Silicone Property; ASTM D412
Elongation at Break	550 %	550 %	Silicone Property; ASTM D412
Peel Strength	1.61 kN/m	9.20 pli	Bond Strength; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	23.0 kV/mm	585 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	120 min Metric	2.00 hour English	Comments
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	Recommended Cure Cycle
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Light Gray	
	White	Substrate
Total Product Weight (oz/yd2)	15.8	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China